

製品名	静電容量値 (μ F/cm ²)								
	Vfs	65.5	73.2	82.7	90.4	105	114	132	143
D670	3.49	3.03	2.58	2.27	1.86	1.64	1.34	1.17	—
D672	4.96	4.31	3.65	3.21	2.61	2.28	1.86	1.61	—
D674	5.82	5.00	4.20	3.68	2.98	2.58	2.04	1.74	—
D676	7.27	6.19	5.12	4.42	3.46	2.96	2.28	1.89	—
U615	8.60	7.34	6.11	5.34	4.16	3.55	2.60	2.15	—
U715	9.70	8.27	6.91	6.02	4.71	4.02	2.96	2.48	—
U815	11.6	9.93	8.29	7.22	5.64	4.77	3.53	2.95	—
U850	12.7	10.6	8.72	7.47	—	—	—	—	—
U750	12.1	10.2	8.26	7.04	—	—	—	—	—
U752	13.4	11.2	9.04	7.57	—	—	—	—	—
U862	13.4	11.2	9.04	7.57	—	—	—	—	—
U854	15.0	12.5	10.1	—	—	—	—	—	—
U953	16.9	14.1	11.1	—	—	—	—	—	—
U873	—	—	—	—	—	—	—	—	—
U974	19.0	—	—	—	—	—	—	—	—
U155	19.0	15.7	12.5	—	—	—	—	—	—
U975	19.7	16.6	13.5	—	—	—	—	—	—
U976	18.5	—	—	—	—	—	—	—	—
U157	20.7	17.0	13.4	—	—	—	—	—	—
U177	20.7	17.0	13.4	—	—	—	—	—	—
U178	23.4	—	—	—	—	—	—	—	—
U198	23.4	—	—	—	—	—	—	—	—
U170	—	—	—	—	—	—	—	—	—
U199	26.8	—	—	—	—	—	—	—	—
U191	28.4	—	—	—	—	—	—	—	—
U846	11.3	9.77	8.25	7.22	5.81	5.01	3.94	3.34	—
U918	13.7	—	10.0	8.82	7.04	6.00	4.70	4.00	—
U919	15.2	—	10.9	9.58	7.63	6.55	5.10	4.40	—
U147	17.5	15.0	12.6	11.0	8.80	7.50	5.65	4.78	3.24
U140	19.1	16.4	13.8	11.9	9.45	8.08	6.10	5.15	3.46
LM108EF2	20.5	17.6	14.7	12.8	10.1	8.59	6.51	5.34	—

1. 低圧陽極用化成箔規格 2/2

製品名	引張り強さ (N/cm)	折曲げ強さ R=0.5mm (回)	容量許容差 (%)	製品厚み ±10% (μm)	原箔 アルミ純度 (%)	標準長さ 〔概略〕 (m)
D670	≧ 22.5	≧ 50	+10, -5	60	≧ 99.98	450
D672	≧ 21.6	≧ 50	+10, -5	60	≧ 99.98	450
D674	≧ 20.6	≧ 50	+10, -5	60	≧ 99.98	450
D676	≧ 21.6	≧ 50	+10, -5	62	≧ 99.98	430
U615	≧ 18.6	≧ 50	+10, -5	65	≧ 99.98	430
U715	≧ 18.6	≧ 50	+10, -5	70	≧ 99.98	400
U815	≧ 19.6	≧ 50	+10, -5	80	≧ 99.98	350
U850	≧ 23.5	≧ 50	+10, -5	80	≧ 99.98	350
U750	≧ 18.6	≧ 50	+10, -5	70	≧ 99.98	400
U752	≧ 18.6	≧ 50	+10, -5	70	≧ 99.98	400
U862	≧ 21.6	≧ 50	+10, -5	80	≧ 99.98	350
U854	≧ 18.6	≧ 50	+10, -5	80	≧ 99.98	350
U953	≧ 18.6	≧ 50	+10, -5	90	≧ 99.98	300
U873	≧ 18.6	≧ 50	+10, -5	80	≧ 99.98	350
U974	≧ 24.3	≧ 50	+10, -5	95	≧ 99.98	300
U155	≧ 18.6	≧ 50	+10, -5	100	≧ 99.98	250
U975	≧ 23.3	≧ 50	+10, -5	95	≧ 99.98	300
U976	≧ 18.6	≧ 50	+10, -5	90	≧ 99.98	300
U157	≧ 18.6	≧ 50	+10, -5	105	≧ 99.98	250
U177	≧ 25.8	≧ 50	+10, -5	100	≧ 99.98	250
U178	≧ 22.5	≧ 50	+10, -5	110	≧ 99.98	250
U198	≧ 18.0	—	+10, -5	110	≧ 99.98	250
U170	≧ 21.6	≧ 50	+10, -5	110	≧ 99.98	250
U199	≧ 17.2	—	+10, -5	120	≧ 99.98	230
U191	≧ 16.7	—	+10, -5	120	≧ 99.98	230
U846	≧ 21.6	≧ 50	+10, -5	80	≧ 99.98	350
U918	≧ 17.6	≧ 50	+10, -5	90	≧ 99.98	300
U919	≧ 17.6	≧ 50	+10, -5	95	≧ 99.98	300
U147	≧ 17.6	≧ 50	+10, -5	100	≧ 99.98	250
U140	≧ 17.6	≧ 50	+10, -5	105	≧ 99.98	250
LM108EF2	≧ 17.6	—	+10, -5	108	≧ 99.98	250

※ 使用される原箔のアルミ純度は、JIS-H-4170、JIS-H-4160 に適用しております。

1. 低圧陽極用化成箔規格 1/2

製品名	静電容量値 (μ F/cm ²)								
	Vfs	8.0	9.9	12.8	15.7	20.5	26.2	32.9	45.6
D670	27.1	22.5	18.1	15.3	12.3	9.72	7.70	5.39	4.81
D672	37.9	31.6	25.4	21.6	17.3	13.8	10.9	7.61	6.81
D674	47.5	39.5	31.8	26.9	21.4	16.9	13.4	9.24	8.20
D676	62.3	53.4	43.1	36.2	28.4	22.3	17.7	11.9	10.5
U615	72.4	61.0	50.0	42.3	33.3	26.0	20.1	13.7	12.1
U715	81.6	68.5	55.5	47.1	37.2	29.1	22.7	15.5	13.7
U815	97.6	83.3	67.7	57.3	45.0	35.0	27.2	18.6	16.5
U850	115	95.5	76.7	64.7	51.4	40.5	31.6	21.2	18.6
U750	119	98.2	78.1	65.4	51.4	40.2	31.1	20.6	18.0
U752	129	109	88.4	74.6	57.8	44.5	34.3	22.6	19.8
U862	129	109	88.4	74.6	57.8	44.5	34.3	22.6	19.8
U854	148	124	100	84.5	66.9	51.4	39.2	25.8	22.6
U953	169	141	114	96.2	76.0	58.3	44.3	29.0	25.4
U873	190	157	125	105	83.3	63.8	48.3	30.9	26.4
U974	185	154	124	105	83.4	64.2	49.7	32.6	28.5
U155	187	156	126	107	85.0	65.3	49.9	32.7	28.5
U975	198	165	132	111	88.2	67.7	52.3	34.1	29.7
U976	212	177	142	119	92.0	71.1	54.0	34.0	29.2
U157	208	175	142	120	95.0	72.7	55.0	35.9	31.3
U177	208	175	142	120	95.0	72.7	55.0	35.9	31.3
U178	233	196	159	136	107	82.6	63.5	40.3	35.1
U198	233	196	159	136	107	82.6	63.5	40.3	35.1
U170	250	208	167	139	108	83.5	63.5	40.0	34.5
U199	271	227	184	158	124	95.8	73.7	46.9	40.6
U191	282	236	191	164	129	99.9	77.0	49.2	42.7
U846	—	—	—	—	—	—	—	—	—
U918	—	—	—	—	—	—	—	—	—
U919	—	—	—	—	—	—	—	—	—
U147	—	—	—	—	—	—	—	—	—
U140	—	—	—	—	—	—	—	—	—
LM108EF2	—	—	—	—	—	—	—	—	—